

Grade: **GLINA MIELONA GM-1/2**
 Product group: AGGREGATES
 Application: component of chamotte masses
 Remarks: -

Properties	Guaranteed	Typical	Unit	Standard
Chemical composition				PN EN ISO 1927-3
	Al ₂ O ₃	30,0	32,0	%
	Fe ₂ O ₃	-	2,3	%
Refractoriness	-	171	sP	PN EN 993-12
Ignition loss	-	14	%	PN EN ISO 12677
Shelf life	no limit		month	

Typical values represent the average of results from the current production. Guaranteed values correspond to mean value due to p. 5.5 of ISO 5022 standard. All values are valid for samples prepared under controlled conditions due to EN ISO 1927-5. Due to p.3.2.2 of ISO 5022 standard the properties which are the criteria of compliance assessment are limited to chemical composition. Properties may be subjected to fluctuations typical of the manufacturing process. PCO reserves the right to modify technical data sheet at any time without prior notice.